



# ROYAL GLOBAL ENERGY

RGE's core business Oil, Gas, Refining and Petrochemicals

## Cutback Bitumen Medium-Curing-30

Properties	Specification Limit		Test Method
	Min	Max	
Kinematic Viscosity at 60 °C ,cSt	30	60	ASTM D2170
Flash Point (Top Open Cup), °C	38	–	ASTM D3143
<b>Distillate, %Volume of Total Distillate to @360 °C</b>			
To 225 °C	–	35	ASTM D402
To 260 °C	40	70	
To 316 °C	75	93	
Residue From Distillation to 360 °C (% Vol by Difference)	50	–	
<b>Test on Residue From Distillation Test</b>			
Penetration, 25 °C, (dmm)	120	300	ASTM D5
Ductility, 25 °C, (cm)	100	–	ASTM D113
Water Content (% Vol)	–	0.2	ASTM D95