



ROYAL GLOBAL ENERGY

RGE's core business Oil, Gas, Refining and Petrochemicals

Pastille Sulfur

Analysis	Unit	Limits
Physical Form	Visual	Pastille
Sulfur	%w/w	99.95% Min
Organic Matter	%w/w	0.015 Max
Ash	%w/w	0.04 Max
Acid	%w/w	0.007 Max
Moisture	%w/w	0.2 Max
As, Se, Te	%w/w	0.0005 Max
Granulation 0.5 to 3.2mm	%w/w	90.00 Min
Bulk Density	Approx. 1200 kg/m ³	